

# TOP GLOVE

## TOP QUALITY, TOP EFFICIENCY

THE WORLD'S LARGEST RUBBER GLOVE MANUFACTURER

### LATEX GLOVE

POWDERED & POWDER-FREE



#### Functional Benefits

- Protection from unwanted or dangerous substances
- Easy donning and helps prevent roll back
- Softness provides superior comfort and natural fit
- Beaded cuff makes donning easy
- Ambidextrous and straight fingers



Latex Glove

# LATEX GLOVE

## POWDERED & POWDER-FREE

### Quality Standards

- Conforms to ASTM D3578 and EN455 Standards.
- Manufactured under QSR (GMP) and ISO9001: 2008 and ISO13485 : 2003 Quality Management System.
- Using FDA approved absorbable corn starch, USP grade.
- Conforms to MDD 93/42/EEC Class I

### Glove Sizes

- Extra-small, Small, Medium, Large, Extra-large.
- Marked in the check box on the shipping carton with black ink.

### Product Specifications

Type	: Powdered & Powder-free; non-sterile
Material	: Natural high quality latex
Design & Features	: <b>Powdered</b> : Ambidextrous; smooth or textured surface; beaded cuff; natural white, coloured or mint flavoured; USP grade absorbable cornstarch <b>Powder-Free (Polymer Coated or Online Chlorinated)</b> : Ambidextrous; smooth or textured surface; beaded cuff; off-white to yellow, coloured or mint flavoured
Storage	: To store in cool and dry condition
Shelf-life	: 5 years from the date of manufacturing

### Physical Dimensions

DIMENSIONS	STANDARDS		
	Top Glove	ASTM D3578	EN455
Length (mm)	Min 240	Min 220 (XS, S) Min 230 (M, L)	Min 240
Width (mm) <ul style="list-style-type: none"><li>• Extra Small</li><li>• Small</li><li>• Medium</li><li>• Large</li><li>• Extra Large</li></ul>	76 ± 3 84 ± 3 94 ± 3 105 ± 3 113 ± 3	70 ± 10 80 ± 10 95 ± 10 111 ± 10 N/A	≤ 80 80 ± 10 95 ± 10 110 ± 10 ≥ 110
Thickness - Single Wall (mm) <ul style="list-style-type: none"><li>• Fingers</li><li>• Palm</li></ul>	Min 0.08 Min 0.08	Min 0.08 Min 0.08	N/A N/A

### Physical Properties

Property	ASTM D3578	EN455
Elongation at Break (%) <ul style="list-style-type: none"><li>• Before Aging</li><li>• After Aging</li></ul>	Min 650 Min 500	N/A N/A
Tensile Strength (MPa) <ul style="list-style-type: none"><li>• Before Aging</li><li>• After Aging</li></ul>	Min 18 Min 14	N/A N/A
Median Force at Break (N) <ul style="list-style-type: none"><li>• Before Aging</li><li>• After Aging</li></ul>	N/A N/A	6 6

If you have any enquiries on our products, please contact:

#### TOP GLOVE SALES & CORPORATE OFFICE

Level 21, Top Glove Tower,  
16, Persiaran Setia Dagang,  
Setia Alam, Seksyen U13,  
40170 Shah Alam,  
Selangor D.E, Malaysia.  
Tel : +603-3362 3098  
Fax : +603-3362 5096 (Sales)  
Email : sales@topglove.com.my



International Quality Certificate Awarded :



<https://www.facebook.com/mytopglove>



[www.topglove.com](http://www.topglove.com)



Top Glove Website

DP/120717TGT